

TECHNICAL DATA SHEET

PS 830

It is neutral hardening Salt used for hardening of Alloy Tool Steel of high carbon & high chromium equivalent of NC-830.

Working Range:- 820-1050C

Density:- 74-75 Kgs/Cuft approx. at 825C

Base : Barium chloride

Physical properties: white crystalline dry powder

Use : Rectifier after 8 hr

Rectifier: base: silicon

Use: 50 Grm for 300 kg of salts for 8 hr.

50 kg packing HDPE bag

